



*Manufacturer
of
Specialty
Chemicals*

GMT-1800 SERIES OF OXIDISED HIGH DENSITY POLYETHYLENE

**High performance lubricants and fusion promoters,
serving the PVC-industry for over 20 years**

Properties	GMT-1807	GMT-1816
Density @23°C (g/cm ³)	0,98	0,98
Acid Number (mgKOH/g)	7	16
Melt Viscosity @180°C (cps)	37.000	11.000
Penetration @23°C (dmm)	< 0,5	< 0,5
DSC Melt Peak (°C)	134,9	134,5
Softening Point (R&B, °C)	134,2	133,8
Saponification Number	14	33

Brought to you by



EURIKAS

WE DEVELOP YOUR BUSINESS!

Mechelsesteenweg 277, B-1800 Vilvoorde, Belgium
+32 2 254 85 45 • BE 0533.923.434 • info@eurikas.com • www.eurikas.com