

HEAD OFFICE: (Hwachi-dong) 342-42, Yeosu, Sandan 1Ro,

Yeosu-si, Chunnam, Korea.

TEL: 82-61-692 - 8300 FAX: 82-61-685 - 8860 SEOUL SALES OFFICE: TEL 82-31-916-6865

TECHNICAL DATA ANALYSIS

Product Name	SUNFOL H-640
Characteristic	Polyethylene wax
CAS NO.	9002-88-4
Concentration	MIN 100%
Appearance	White powder
Melt Viscosity	400 ± 100cPs (@140°C)
Density	0.95 ±0.02 (@25°C,g/cm²)
Softening Point	120 ± 3°C (Ring&Ball)
Hardness	Max 2.0 (0.1mm)
Toxicology	Oral-mouse LD50 : 3 mg/kg
Field Of Application	Pigment dispersing agent for plastic high concentrate
	(master batch), External lubricant for PVC extrusion
	processing, Wear resistance improver of paints and
	inks, Engineering plastic lubricants, Hot-melt process
	ability improver, paper coating agent, rubber process
	ability improver, Improver of various waxes' fusion point

Authorized By: Y. H. PARK

Q.C Dept. manager