

## WIWAX POLYETHYLENE WAX

### WIRATEN 82

Parameter	Standard	Unit of measure	Requirement
Penetration at 25 °C	PN-82/C-04161 & ASTM D.1321	0,1 mm	8 - 12
Drop Point	PN-55 C-04020	°C	99 - 106
Solidification point	PN-82 C-04022	°C	87 - 93
Viscosity at 140 °C	PN-EN ISO 3219	cP	< 15
Presentation	White to off white prills		