

WIWAX POLYETHYLENE WAX

WIRATEN 95

Parameter	Standard	Unit of measure	Requirement
Penetration at 25°C	PN-82/C-04161 & ASTM D.1321	0,1 mm	12 - 18
Drop Point	PN-55 C-04020	°C	102 - 112
Solidification point	PN-82 C-04022	°C	90 - 98
Viscosity at 140 °C	PN-EN ISO 3219	cP	< 40
Presentation	White to off white prills		